



TECHNICAL DATA

GB UNIGREASE® 1725

GB UNIGREASE® 1725 is a premium quality water resistant grease for use in all anti-friction and plain bearings subjected to high load and extremely wet or even saturated operating conditions. GB UNIGREASE® 1725 finds use in many industries such as agricultural, construction, forestry, industrial, marine and steel.

COST SAVING BENEFITS

- Excellent water resistance, ensuring maximum grease life and extending lubrication intervals
- Dewatering properties enabling application to wet surfaces
- Anti-corrosion agents, protecting and extending the working life of components
- Extreme Pressure (EP) additives, providing protection against premature wear
- Excellent resistance to oxidation ensuring long lubricant life

METHOD OF APPLICATION

GB UNIGREASE® 1725 can be applied by hand, or by using a standard grease gun (400gm cartridges are available), or via a central lubricating system capable of pumping an NLGI No 2 grease.

TYPICAL PHYSICAL CHARACTERISTICS

Appearance	-	Brown, tacky grease
NLGI Classification	-	2
Thickener	-	Aluminium complex
Base Oil	-	Mineral oil
Base Oil Viscosity @ 40°C (ASTM D445)	-	100 cSt
Dropping point (ASTM D2265)	-	250°C min.
Water washout @ 79°C (ASTM D1264)	-	3%
Copper corrosion (ASTM D4048)	-	1a
Four Ball Weld Load (IP 239)	-	250 kgf
Operating Temperature Range	-	-30°C to +150°C

Cont'd.../...

GB LUBRICANTS

Albany Road Gateshead NE8 3BP

Tel: 0191 490 4312
Fax: 0191 477 9544
e-mail: gblsales@gb lubricants.co.uk
www.gblubricants.co.uk

Trading Name of Goodall Bates & Todd Ltd



GB LUBRICANTS

STORAGE AND HANDLING

GB UNIGREASE® 1725 should be stored under cover to avoid water collecting in the rim of upturned pails. Ideal storage temperature between 0°C and 25°C, away from moisture and direct sources of heat or sunlight.

Further information on GB UNIGREASE® 1725 can be obtained by referring to the corresponding Safety Data Sheet.

The Company policy is to ensure that a range of products is supplied which complies with the latest specifications and codes within the relevant industry. As part of this development process, we therefore reserve the right to amend formulations without prior notice.