



TECHNICAL DATA

GB UNIGREASE® C2

GB UNIGREASE® C2 is a premium quality, water resistant grease for use in industrial, automotive and marine applications where the presence of water and humid atmospheres can affect lubricating performance and be detrimental to the protection of parts from corrosion. GB UNIGREASE® C2 is suitable for plain and anti-friction bearings.

PERFORMANCE FEATURES

- High degree of water resistance
- Excellent corrosion protection
- Good sealing properties

METHOD OF APPLICATION

GB UNIGREASE® C2 can be applied manually, or by using a standard grease gun or via a central lubricating system designed for and capable of pumping an NLGI No.2 grease; consult a qualified centralised lubrication systems engineer before installation. As with all greases used for the first time, check compatibility with the grease applied previously and if necessary purge bearings prior to application. Likewise, as a general rule, take care not to over-lubricate and apply the quantity of grease recommended by the bearing manufacturer.

TYPICAL PHYSICAL CHARACTERISTICS

Appearance	- Smooth brown grease
NLGI classification	- 2
Thickener	- Calcium
Base oil	- Mineral oil, 100 cSt
Dropping point (ASTM D2265)	- 140°C min
Water washout @ 79°C (ASTM D1264)	- 2.3%
Copper corrosion (ASTM D4048)	- 1b
Resistance to corrosion EMCOR (ASTM D6138)	- 0:0
Operating Temperature Range	- -30°C to +110°C

Cont'd.../...

GB LUBRICANTS

Albany Road Gateshead NE8 3BP

Tel: 0191 490 4312
Fax: 0191 477 9544
e-mail: gblsales@gb lubricants.co.uk
www.gblubricants.co.uk

Trading Name of Goodall Bates & Todd Ltd



GB LUBRICANTS

STORAGE AND HANDLING

GB UNIGREASE® C2 should be stored under cover to avoid water collecting in the rim of upturned pails. Ideal storage temperature between 0°C and 25°C, away from moisture and direct sources of heat or sunlight.

Further information on GB UNIGREASE® C2 can be obtained by referring to the corresponding Safety Data Sheet.

The Company policy is to ensure that a range of products is supplied which complies with the latest specifications and codes within the relevant industry. As part of this development process, we therefore reserve the right to amend formulations without prior notice.